

ESTERDAN 50/GP POL GREEN GARDEN

ESTERDAN 50/GP POL GREEN GARDEN is a waterproofing bituminous sheet with self-protected surface of 5 kg/m², LBM-50/G-FP R (APP -15 °C).

Composed of a reinforced polyester felt reinforcement, covered on both sides with polymer modified bitumen mastic. On the upper side of the sheet, mineral protection in green. The anti-adhesive material used on the lower side is polyethylene film. Bitumen is treated with special additives in order to deter root damage.

Tested according to standard EN test methods.



CE MARKING



Identification number of the Certification Body: 0099

DERIVADOS ASFALTICOS NORMALIZADOS S.A.
Calle La Granja 3 (28108 - Alcobendas, MADRID)

Year in which the CE marking was affixed: 2011
Certificate number CPF: 0099 / CPD / A85 / 0013
European standard UNE-EN 13707.

Produced at: Polígono Industrial Sector 9 (19290 - FONTANAR, Guadalajara)

Membrane of 1 m x 8 m x 5 kg/m² composed of polymer modified bitumen with reinforced and stabilized polyester felt. Membrane with an upper surface finish of mineral granules and a lower surface finish of polyethylene film. Torch-on application.

TECHNICAL DATA	VALUE	UNIT	STANDARD
External fire performance	Broof(t1)	-	UNE-EN 1187; UNE-EN 13501-5
Reaction to fire	E	-	UNE-EN 11925-2; UNE-EN 13501-1
Watertightness	Pasa	-	UNE-EN 1928
Longitudinal tensile strength	700 ± 200	N/5cm	UNE-EN 12311-1
Transversal tensile strength	450 ± 150	N/5cm	UNE-EN 12311-1
Longitudinal elongation at break	45 ± 15	%	UNE-EN 12311-1
Transversal elongation at break	45 ± 15	%	UNE-EN 12311-1
Resistance to root penetration	Pasa	-	UNE-EN 13948
Resistance to static loading	>15	kg	UNE-EN 12730
Resistance to impact	>1000	mm	UNE-EN 12691
Longitudinal resistance to tearing (nail shank)	220 ± 40	N	UNE-EN 12310-1
Transversal resistance to tearing (nail shank)	220 ± 40	N	UNE-EN 12310-1
Joint strength: peel resistance	PND	-	UNE-EN 12316-1
Joint strength: shear resistance	450 ± 150	-	UNE-EN 12317-1
Flexibility at low temperature	< -15	°C	UNE-EN 1109
Humidity resistance factor	20.000	-	UNE-EN 1931
Dangerous substances	PND	-	-
Flexibility at low temperature (pliability)	-5 ± 5	°C	UNE-EN 1109
Flow resistance at elevated temperature	120 ± 10	°C	UN-EN 1110

Pasa = Positive or correct No pasa = Negative PND = No performance determined - = Not necessary

ADDITIONAL TECHNICAL DATA

ADDITIONAL DATA	VALUE	UNIT	STANDARD
Mass per unit area (nominal)	5	kg/m ²	-
Mass per unit area (minimum)	4.75	kg/m ²	-
Nominal thickness	3.5(SOLAPO)	mm	-
Flow resistance at elevated temperature	> 130	°C	UN-EN 1110
Dimensional stability at elevated temperature (longitudinal)	< 0.3	%	UNE-EN 1107-1
Dimensional stability at elevated temperature (transversal)	< 0.3	%	UNE-EN 1107-1
Adhesion of granules	< 30	%	UNE-EN 12039

Membranes thickness tolerance: = -0,3 mm, apart from membranes with thickness 2 and 2,4 mm whose tolerance is = -0,2 mm

DECLARATION OF CONFORMITY



DERIVADOS ASFÁLTICOS NORMALIZADOS S.A.
Calle La Granja 3 (28108 - Alcobendas, MADRID)

Membrane of 1 m x 8 m x 5 kg/m² composed of polymer modified bitumen with reinforced and stabilized polyester felt. Membrane with an upper surface finish of mineral granules and a lower surface finish of polyethylene film. Torch-on application.

This product is according to the Z.A. Annex of the UNE-EN 13707.


The roll must be stored upright and it has to be pulled for the opposite side to the overlap band. These rolls have to be protected against atmospheric conditions and dampness. The Application cannot be done under temperatures lower than -5 °C.

Certificate number CPF: 0099 / CPD / A85 / 0013

José Antonio Manzarbeitia Valle
Manager Quality and R&D Manager.
Fontanar, December 12 2011

PRESENTATION

PRESENTATION	VALUE	UNIT
Length	8	m
Width	1	m
Roll surface	8	Product Code
Rolls per pallet	25	rolls
Product Code	141983	-


WARNING

The information that appears in the following document makes reference to the uses and utilities of danosa's products and systems, and it is based on the knowledge that have been learnt until present, by Danosa. This is only possible if products have been stored and used in an appropriate way.

Nevertheless, Danosa is not responsible for unsuitable uses of the products neither any other facts, such as meteorological facts. So Danosa is just responsible for the quality related to the provided products.

Danosa reserves the right to carry out modifications without previous notice.

The values that appear in the technical sheet are the results of the tests that have been performed in our laboratory. Decembre 2011.

Web site: www.danosa.com E-mail: export@danosa.com Phone number: +34 949 888 210